

45/35BL

L/d

Length

Bright

Loose

DATASHEET

Characteristics

Material properties


Nom. tensile strength: 1.200 (N/mm²)

Young's modulus: 200.000 (N/mm²)


Strain at ultimate strength: 0,8 %

Geometry

Length (l) 35 mm



Diameter (d) 0,75 mm



Aspect ratio (l/d) 45

Minimum EN 14889-1 dosage

35 kg/m³

Product certificates



Product conformity

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

Packaging



BAGS
20 kg



BIG BAG
800 kg

Handling



For recommendations on handling, dosing and mixing visit www.bekaert.com/dosingdramix. Any other specific document or certificate can be found on www.bekaert.com/doc/BSF



BEKAERT STEEL FIBRES 45/35BL

Bekaert Steel Fibres are filaments of wire, deformed and cut to lengths for reinforcement of concrete.

BEKAERT CONSTRUCTION SUPPORT

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team. Feel free to ask us for a workshop or training on the topic of steel fibre reinforcement in your offices.