



45 / 35 BL

Aspect ratio

Length

Bright

Loose

DATASHEET

Characteristics

Material properties

Nom. tensile strength: 177.671229 ksi (1225 MPa)
 Young's modulus: 29000 ksi (200000 MPa)
 Strain at ultimate strength: 0.8 %

Geometry

Fiber family **3D**

Length (l) 1.38 in. (35 mm)

Diameter (d) 0.029528 in. (0.75 mm)

Aspect ratio (l/d) 45

Minimum EN 14889-1 dosage

51 lb/yd³ (30 kg/m³)

Fiber network

21668 ft/yd³ at 51 lb/yd³ (8639) m/m³ at 30 kg/m³
 3588 fibers/lb (7911 fibers/kg)

Dramix® family

3D Typical SFRC applications
 4D Supreme serviceability control
 5D Advanced structural applications

	5D	4D	3D
Tensile strength			
Wire ductility			
Anchorage strength			

Product certificates*



* Product certificates are plant specific.

Product conformity

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

System certificates



All Dramix® plants are ISO 9001 and ISO 14001 certified.

Packaging



BAGS
 44 lb (20 kg)



BIG BAG
 1,760 lb (800 kg)

Handling



DRAMIX® 3D 45/35BL

The original anchorage

Dramix® 3D is the cost-efficient fiber for standard statically indeterminate concrete structures that are submitted to regular static, fatigue and dynamic loadings.

Bekaert Bekaert construction support

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team.

Feel free to ask us for a workshop or training on the topic of steel fiber reinforcement in your offices.

For recommendations on handling, dosing and mixing visit www.bekaert.com/dosingdramix. Any other specific document or certificate can be found on www.bekaert.com/dramix/downloads.