BEKAERT

better together





65/35 BG

Length

Aspect ratio

DATASHEET

Characteristics

Material properties

Nom. tensile strength:	195.075758 ksi (1345 MPa)
Young's modulus:	29000 ksi (200000 MPa)
Strain at ultimate strength:	0.8 %

Geometry

Fiber family

Length (I)

1.38 in. (35 mm)

Diameter (d) 0.021654 in. (0.55 mm)

Aspect ratio (I/d) 65



Minimum EN 14889-1 dosage

25 lb/yd³ (15 kg/m³)

Fiber network

20146 ft/yd3 at 25 lb/yd3 (8032) m/m3 at 15 kg/m3) 6672 fibers/lb (14711 fibers/kg)

Dramix[®] family

3D Typical SFRC applications 4D Supreme serviceability control 5D Advanced structural applications



Product certificates*



* Product certificates are plant specific.

Product conformity

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

System certificates



All Dramix® plants are ISO 9001 and ISO 14001 certified.

Packaging



BAGS 44 lb (20 kg)



Handling



DRAMIX® 3D 65/35BG

The original anchorage

Bright

Dramix[®] 3D is the cost-efficient fiber for standard statically indeterminate concrete structures that are submitted to regular static, fatigue and dynamic loadings.

Glued

Glue technology for three-dimensional reinforcement

Dramix[®] steel fibers are bundled with water-soluble glue. The glue helps avoiding fiber balling during mixing and ensures a homogeneous distribution of fibers throughout the concrete mix.

Bekaert Bekaert construction support

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team

Feel free to ask us for a workshop or training on the topic of steel fiber reinforcement in your offices.



Bekaert reserves the right to modify, discontinue or rebrand this product at any time with or without notice. All information contained herein is general and may not be complete. For further details, please contact the local Bekaert office.