



**4D**  
Dramix®

**55 / 61 BL**

Aspect ratio

Length

Bright

Loose

**DATASHEET**

**Characteristics**

**Material properties**

Nom. tensile strength:	210.30472 ksi (1450 MPa)
Young's modulus:	29000 ksi (200000 MPa)
Strain at ultimate strength:	0.8 %

**Geometry**

Fiber family	<b>4D</b>	
Length (l)	2.40157 in. (61 mm)	
Diameter (d)	0.041339 in. (1.05 mm)	
Aspect ratio (l/d)	55	

**Minimum EN 14889-1 dosage**

30 lb/yd<sup>3</sup> (18 kg/m<sup>3</sup>)

**Fiber network**

6631 ft/yd<sup>3</sup> at 30 lb/yd<sup>3</sup> (2644 m/m<sup>3</sup> at 18 kg/m<sup>3</sup>)  
1049 fibers/lb (2313 fibers/kg)

**Dramix® family**

- 3D Typical SFRC applications
- 4D Supreme serviceability control
- 5D Advanced structural applications

	5D	4D	3D
Tensile strength			
Wire ductility			
Anchorage strength			

**Product certificates\***



\* Product certificates are plant specific.

**Product conformity**

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

**System certificates**



All Dramix® plants are ISO 9001 and ISO 14001 certified.

**Packaging**



**BAGS**  
44 lb  
(20 kg)



**BIG BAG**  
2,420 lb  
(1,100 kg)

**Handling**



**DRAMIX® 4D 55/60BL**

**Optimized anchorage**

Dramix® 4D provides optimal crack control for standard statically indeterminate concrete structures that are submitted to regular static, fatigue and dynamic loadings with high serviceability requirements.

**Bekaert Bekaert construction support**

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team.

Feel free to ask us for a workshop or training on the topic of steel fiber reinforcement in your offices.