# **BEKAERT**

better together





# 65/61 BG

Length

Aspect ratio

# DATASHEET

# Characteristics

### **Material properties**

Nom. tensile strength:	232.060381 ksi (1600 MPa)
Young's modulus:	29000 ksi (200000 MPa)
Strain at ultimate strength:	0.8 %

(61 mm)

(0.9 mm)


### Geometry

Fiber family

Length (I) 2.40157 in.

Diameter (d)0.035433 in.

Aspect ratio (I/d) 65



# Minimum EN 14889-1 dosage


25 lb/yd<sup>3</sup> (15 kg/m<sup>3</sup>)

### **Fiber network**

7522 ft/yd3 at 25 lb/yd3 (2999) m/m3 at 15 kg/m3) 1428 fibers/lb (3149 fibers/kg)

### **Dramix**<sup>®</sup> family

**3D** Typical SFRC applications 4D Supreme serviceability control 5D Advanced structural applications



# Product certificates\*



\* Product certificates are plant specific.

# Product conformity

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

# System certificates



All Dramix® plants are ISO 9001 and ISO 14001 certified.

**BIG BAG** 

2.420 lb

(1.100 kg)

# Packaging



BAGS 22 / 44 lb (10 / 20 kg)

# Handling



# **DRAMIX® 4D 65/60BG**

### **Optimized anchorage**

Bright

Dramix<sup>®</sup> 4D provides optimal crack control for standard statically indeterminate concrete structures that are submitted to regular static, fatigue and dynamic loadings with high serviceability requirements.

Glued

### Glue technology for three-dimensional reinforcement

Dramix<sup>®</sup> steel fibers are bundled with water-soluble glue. The glue helps avoiding fiber balling during mixing and ensures a homogeneous distribution of fibers throughout the concrete mix.

### Bekaert Bekaert construction support

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team.

Feel free to ask us for a workshop or training on the topic of steel fiber reinforcement in your offices.

For recommendations on handling, dosing and mixing visit www.bekaert.com/dosingdramix. Any other specific document or certificate can be found on www.bekaert.com/dramix/downloads.

